



CLARITY[®] SYNTHETIC EA GREASE

PRODUCT DESCRIPTION

Chevron's Clarity[®] Synthetic EA Grease is an anhydrous calcium-thickened lubricating grease based on biodegradable esters. The grease contains antioxidants, corrosion inhibitors, and EP/W additives. The thickener, together with the biodegradable esters, makes the product suitable for lubrication of heavily loaded applications. The lubricating grease has excellent adhesion and water resistance.

Clarity Synthetic EA Grease is readily biodegradable, has excellent water resistance, good corrosion resistance and is excellent for extreme pressure and heavy loads. It is compliant to 2013 VGP legislation and the Swedish Standard 155470. It is pumpable in most modern centralized lubrication systems.

CUSTOMER BENEFITS

Clarity Synthetic EA Grease delivers value through:

- **Environmentally acceptable** — Meets the requirements of the EPA Vessel General Permit (VGP) for biodegradation, low toxicity and low bioaccumulation.
- **Water resistance** — Provides satisfactory lubrication in the presence of water and is not washed out of bearings.
- **Corrosion protection** — Rust-inhibited to protect steel and nonferrous-bearing surfaces against corrosion.
- **Multipurpose** — Satisfies all grease requirements of the majority of marine equipment.
- **Pumpability** — Can be used over a wide temperature range in centralized lubrication systems.

APPLICATIONS

Clarity Synthetic EA Grease is suitable for on-deck applications including wire ropes, rudder posts, closed shaft with grease, valves, valve spindles, doors, various bearing applications on spindles, and lifeboat davit.

TYPICAL TEST DATA

Product Number	238009
SDS Number	39898
Viscosity, Kinematic (ASTM D445, DIN 51562-1) cSt at 40°C cSt at 100°C	500.0 53.0
Operating Temperature Range, °C	-40 to 100
Penetration at 25°C (ASTM D217)	265-295
Dropping Point, °C (ASTM D2265, IP 396)	> 140
Four-ball Weld Load, kg (ASTM D2596, DIN 51350:4)	305
Water Resistance at 90°C (ASTM D4049, DIN 51807:1)	0
Water Washout at 38°C (ASTM D1264, ISO 11009)	<10%
Thickener Type	Anhydrous Calcium
Base Fluid	Ester
Texture	Smooth
Color	Yellow

Minor variations in product typical test data are to be expected in normal manufacturing.

Product(s) manufactured in the USA.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.

A **Chevron** company product

13 March 2017
GR-50

© 2017 Chevron U.S.A. Inc. All rights reserved.

Chevron, the Chevron Hallmark and Clarity are trademarks owned by Chevron Intellectual Property LLC. All other trademarks are property of their respective owners.

Always confirm that the product selected is consistent with the original equipment manufacturer's recommendation for the equipment operating conditions and customer's maintenance practices.

13 March 2017
GR-50

